(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 3 May 2001 (03.05.2001)

PCT

(10) International Publication Number WO 01/30886 A2

(51) International Patent Classification?: C

C08G 77/38

(21) International Application Number: PCT/US00/41558

(22) International Filing Date: 26 October 2000 (26.10.2000)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

09/427,216

26 October 1999 (26.10.1999) US

- (71) Applicant (for all designated States except US): MONA INDUSTRIES, INC. [US/US]; 76 East 24th Street, Paterson, NJ 07544 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): GORMLEY, John, L. [US/US]; 52 Hillside Avenue, Midland Park, NJ 07432 (US). BERGER, Abe [US/US]; 11 Malvern Drive, Summit, NJ 07901 (US). FOST, Dennis, L. [US/US]; 208 Van Dien Avenue, Ridgewood, NJ 07450 (US).

- (74) Agents: SHARER, Paul, L. et al.; Pillsbury Madison & Sutro, LLP, 1100 New York Avenue, N.W., Washington, DC 20005 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

 Without international search report and to be republished upon receipt of that report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

A2

(54) Title: ZWITTERIONIC SILOXANE POLYMERS AND IONICALLY CROSS-LINKED POLYMERS FORMED THERE-FROM

(57) Abstract: Ionically cross-linked silicone polymers of a thickened gel-like consistency are made by reacting a diamino containing polysiloxane with an acid containing reactant selected from itaconic acid or the ester derivative thereof; substituted or unsubstituted cyclic and ankydride; substituted or unsubstituted conjugated olefinic acid or mixtures of the same at an elevated temperature in the presence of a low molecular weight silicone oil or other solvent until an ionically cross-linked zwitterionic siloxane polymer of a gel-like consistency is formed.